



Technical Data Sheet

CG52B Contact Treatment Grease

Product Description

The CG series of Contact Lubricants is an extension of the extremely popular 2X range. The main advantages of these products are reduced contact resistance (even on extremely heavy usage), improved plastics compatibility and improved mechanical lubrication.

CG52B is suitable for use on either moving or static contacts of all metal types.

The unique properties of CG52B have been produced by using a blend of low viscosity base oils, containing anti-corrosion, anti-oxidant and metal protection additives, thickened with a complex soap. The use of a complex soap thickener, rather than clay or silica, has the benefit of producing smoother grease with superior mechanical properties. These include decreasing wear and producing a high quality switch "feel". In addition if the switch is exposed to extremely high temperatures over long periods, forcing the base oil to evaporate, the thickener will not remain as an insulative, abrasive layer on the contact surfaces.

Features

- Extends switch lifetime
- Produces low and constant mV drop (and contact resistance)
- Wide operating temperature range
- Optimal mechanical resistance
- Reduces electrical background noise
- Provides smooth, high quality switch "feel"

Approvals	RoHS Compliant (2002/95/EC):	Yes
Typical Properties:		
Colour		Light Brown
Density (g/ml)		0.995
Temperature Range (°C)		-45 to +130
Evaporation Weight Loss (% 7 days @ 100°C)		2.21
Evaporation Weight Loss (% 7 days @ 125°C)		3.77
Copper Strip Corrosion (IP154 / ISO 2160)		≤1b
Drop Point (IP32 / ISO 2176 (°C)		>230
Cone Penetration Worked (ASTM D217, 60 strokes @ 20°C)		320
Cone Penetration Un-Worked (ASTM D 217 @ 20°C)		310
Cone Penetration Un-Worked (ASTM D 217 @ -40°C)		210
Consistency (NLGI)		1
Fliessdruck (Flow Pressure) (DIN 51805, mbar @ -40°C)		345
Oil Bleed / Separation (IP121)		5%
Silver Corrosion (DIN 51759, 3 hrs @100°C)		No change

Plastic Compatibility – ABS
Plastic Compatibility – PC
Thickener
UV Trace

Test
Test
Lithium Complex Soap / Clay
No

Base Oil Properties:

Base Oil Type	Complex Ester
Pour Point (ASTM D 97 (°C))	-45
Flash Point (COC ASTM D 92 (°C))	230

<u>Packing</u>	<u>Order Code</u>	<u>Shelf Life</u>	<u>Container Dimension</u>
35ml Syringe	CG52B35SL	48 months	
1 Kg Bulk	CG52B01K	72 months	
5 Kg Bulk	CG52B05K	72 months	
12.5 Kg Bulk	CG52B12.5K	72 months	254mm (inside diameter) x 330mm (height)
25 Kg Bulk	CG52B25K	72 months	305mm (inside diameter) x 406mm (height)

The 12.5 and 25 kg grease drums have parallel sides for use with “follower plate” dispensing equipment for automated manufacturing lines.

Directions For Use

Before final treatment with Electrolube lubricants, contact surfaces should be clean and dry. For general removal of dirt, Electrolube Ultrasolve is recommended. Hardened dirt and tarnish, especially on larger contacts, should be removed by rubbing with an abrasive material, which can be impregnated with the lubricant to be used.

After cleaning non-wiping contacts, loosened tarnish should be removed before a final application of lubricant is made. Electrolube Contact Cleaning Strips (CCS) are recommended for this purpose. With wiping contacts, loosened tarnish will be pushed aside. This can be removed if desired, but is usually not necessary, due to the excellent lubricating and protective properties of the contact lubricant.

CG52B can be applied by one of the following methods (although this list is not exhaustive):

Manually by way of a syringe

Semi-automated using syringe dispensing equipment

Fully automated by way of a follower/pusher plate with dispensing system.

Typical Product Applications

CG52B has been particularly successful for use as a connector lubricant for automotive wiring looms. This reduces background noise and ensures on-board computers, engine management systems etc. are not affected by electrical spikes.

Copyright Electrolube 2011

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification.

Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.