

STATICIDE ULTRA II FLOOR FINISH

Product Code: E48001UF

PRODUCT DESCRIPTION

Newly designed **Staticide Ultra II** protects static dissipative tiles from soiling, imparts a high gloss, and controls static charge generation and dissipation.

PRODUCT USE

An ideal product wherever static is a problem or sensitive equipment is present on static dissipative floor tiles.

FEATURES

- * Non-flammable
- * UV Resistant
- * High Gloss
- * Formulated to increase life of ESD tiles and aid in black mark removal

TOXICITY AND MATERIAL SAFETY

In use **Staticide Ultra II Floor Finish** is safe. In bulk this product is classed as harmful.

TYPICAL PROPERTIES

Density:	1.0
Boiling Point:	100°C
Freezing Point:	Variable
Solubility in Water	Miscible
Odour:	Mild Odour
pH:	7.0 – 9.5
% Volatile:	65
Physical State:	Liquid
Appearance:	Clear or Translucent

TECHNICAL
DATA
SHEET



**Copyright
Electrolube
2003**

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.



STATICIDE ULTRA II FLOOR FINISH – Page 2

DIRECTIONS FOR USE

1. Strip floors prior to applying **Staticide Ultra II**.
2. Rinse twice with clean water in order to remove any residual stripper solution which will not allow the floor finish to cure properly.
3. Apply two thin coats of **Staticide Ultra II**. Use a clean, lint-free rayon string mop that has been rinsed in fresh water then squeezed almost dry. Polish one small section at a time, no longer than 3 metres. **DO NOT** overlap freshly polished areas.
4. Wait a minimum of 1 hour between each coat. Polish must be completely cured before applying the next coat. Normal traffic may resume in 6-8 hours (preferably overnight) after applying the third coat.
5. Wait 72 hours. Sweep, damp mop with 1 to 1 dilution of **Staticide Ultra II** with water, and let floor dry 1 hour before applying coats 4 & 5. Wait at least 3-5 hours between coats. Normal traffic may resume in 6-8 hours (preferably overnight) after applying the final floor finish coat.
6. **DO NOT** perform any additional wet maintenance procedure until the last coat of **Staticide Ultra II** has cured for a minimum of 72 hours.

PACKAGING

1 Gallon (US) (3.75 Litres)

ORDER CODE

E48001UF



This product is distributed on behalf of ACL Staticide, 1960 East Devon Avenue, EIK Grove Village, IL 60007 USA. An ISO9002 certified company.

Tel: 847 981 9212 Fax: 847 981 9278 Website: www.aclstaticide.com

TECHNICAL DATA SHEET



Copyright Electrolube 2003

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.

