

MOLYKOTE® P-1042 Adhesive Grease Paste

Light-colored grease-paste fortified with solid lubricants; provides excellent adhesion on metallic surfaces

Features

- High load-carrying capacity
- Outstanding resistance to washout by water and metal machining emulsions
- Avoids tribo-corrosion
- Prevents stick-slip
- Excellent protection against galling
- High tack for extended durability
- No intentional polytetrafluoroethylene (PTFE) or per- and polyfluoroalkyl substances (PFAS)

Composition

- Mineral and synthetic base oils
- Lithium soap
- Solid lubricants
- Adhesion improver
- Corrosion protection

Applications

Harsh metal-to-metal applications where high loads, temperatures and/or humidity are present. Sliding surfaces exposed to high-pressure loadings and subjected to the influence of water emulsions of metal machining as found in clamping tools.

How to use

Clean the contact areas. Apply with brush, spatula, grease gun or automatic lubricating device. Can be used in central lubrication systems.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

| Standard ⁽¹⁾ | Test | Unit | Result |
|-------------------------|--|--------------------|--------------------------|
| | Color | | Light beige |
| DIN 51818 | NLGI Class | | 1-2 |
| ISO 2137 | Worked penetration | mm/10 | 285-320 |
| ISO 2811 | Density at 20°C | g/ml | 1.28 |
| | Service temperature as paste | °C | -25 to +120 |
| | as solid lubricant | °C | + 500 |
| ISO 2176 | Drop point | °C | > 150 |
| ASTM D1478-80 | Low-temperature torque test at -20°C | | |
| | Initial break-away torque | Nm | < 300 x 10 ⁻³ |
| | Torque after 20 min running time | Nm | < 100 x 10 ⁻³ |
| DIN 51805 | Kesternich flow-pressure at -25°C | mbar | < 1,800 |
| DIN 51350 pt.4 | Four-ball tester weld load | N | 9,000 |
| DIN 51350 pt.5 | Four-ball tester wear scar under 800 N load | mm | 0.75 |
| | Press-fit test | μ | 0.1 |
| | Friction coefficient of bolt connection ¹ | μ thread μ bolt | 0.11 0.12 |
| DIN 51807 pt.1 | Water resistance, static (90°C, 3 h) | | 0-90 |
| DIN 51807 pt.2 | Water washout (80°C, 1 h) | wt.-% | < 5 |
| DIN 51 802 | SKF-Emcor method Degree of corrosion | | 0-1 |

⁽¹⁾DIN: Deutsche Industrie Norm. ISO: International Organization for Standardization. ASTM: American Society for Testing and Materials.

⁽²⁾Tested on Schatz screw tester with M12x1.75, blackened 8.8 bolts.

Usable life and storage

When stored between 0°C and 40°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes as shown on [molykote.com](https://www.molykote.com). Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2020-2024 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.