



MOLYKOTE® P-3300 Paste

Preliminary data

Anti-seize paste for assembly and threaded connections

Features

- Constant and defined friction on threaded connections
- Wide service temperature range
- Good water resistance
- Good corrosion inhibition properties
- No intentional calcium ingredients
- No intentional polytetrafluoroethylene (PTFE) or per- and polyfluoroalkyl substances (PFAS)

Composition

- Mineral oil
- Solid lubricants
- Thickener
- Corrosion inhibitor

Applications

Suitable for lubrication of threaded connections up to service temperatures of 540°C. Paste has been developed for friction control on a constant level, targeting friction class B of VDI 2230. Paste guarantees safe operation at elevated temperatures due to no intentional added calcium compounds, which are known to promote formation of hexavalent chromium compounds at high temperatures.

How to use

Clean points of contact. In case of visible oil separation, stir up product before use. Apply in same way as lubricating greases, using brush, spatula or grease-gun. Suitable for delivery by central lubricating system.

Do not mix with other lubricants, as this may have adverse effects on consistency and performance.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

| Standard ⁽¹⁾ | Test | Unit | Result |
|--|--|-------|-------------|
| | Color | | White |
| Consistency, density, viscosity | | | |
| ISO 2137 | Unworked penetration | mm/10 | 280 - 320 |
| ISO 2811 | Density at 20°C | g/ml | 1.54 |
| Temperature | | | |
| | Service temperature range | °C | -30 to +540 |
| | Stability of solid lubricant | °C | +1350 |
| DIN 51 805 | Kesternich method - flow pressure at -30°C | mbar | < 1400 |
| Threaded Connections | | | |
| Internal | Bolted connection test: Schatz Tester | | |
| | M12 x 1.75 mm, 8.8, blackened surface | | |
| | μ thread avg. (min.) | | 0.13 (0.10) |
| | μ head avg. (min.) | | 0.11 (0.10) |
| | k-factor avg. | | 0.16 |
| | M12 x 1.75 mm, A2-70, 1.4301, blank | | |
| | μ thread avg. (min.) | | 0.13 (0.11) |
| | μ head avg. (min.) | | 0.11 (0.10) |
| | k-factor avg. | | 0.16 |
| | M12 x 1.75 mm, 1.7709, blank | | |
| | μ thread avg. (min.) | | 0.11 (0.10) |
| | μ head avg. (min.) | | 0.12 (0.11) |
| | k-factor avg. | | 0.16 |
| Internal | Initial breakaway torque after 540°C / 21 h on 1.7709, M12, blank (start torque = 56 Nm) | Nm | ~130 |

⁽¹⁾ISO: International Standardization Organization. DIN: Deutsche Industrie Norm.

Continued on next page.

Typical properties (continued)

| Standard ⁽¹⁾ | Test | Unit | Result |
|--|--|-------|--------|
| Corrosion protection & Water Resistance | | | |
| DIN 51 807 T.1 | Water resistance, static evaluation step | | 0-90 |
| DIN 51 807 T.2 | Water washout (80°C, 1 h) | wt.-% | < 5 |
| ASTM D 130 | Copper Corrosion, 24h / 100°C | | 1a |
| DIN 51 802 | SKF-Emcor method – distilled Water Degree of corrosion | | ≤ 2 |

⁽¹⁾ISO: International Standardization Organization. DIN: Deutsche Industrie Norm. ASTM: American Society for Testing and Materials.

Usable life and storage

When stored between 0°C and 40°C in the original unopened containers, this product has a usable life of 36 months from the date of production.

Packaging

This product is available in different standard container sizes as shown on molykote.com. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1997-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.