

# TECHNICAL DATASHEET

# Vitralit® UD 8559

Vitralit UD8559 is for Bonding / sealing /potting of plastics, glass, metal or FR4, protection of sensitive components against mechanic and environmental stresses. Vitralit UD8559 adheres quite well to untreated PP. Possible use for Pin-Sealing or the protection of components on circuit boards.

In shadow areas, the product cures with air moisture. After UV / light curing surface is immediately dry and tackfree and the product provides high strength. Final, very high performance will be achieved after a few days.

Storage Stability: 3 months at room temperature, slightly raise of viscosity possible

#### Shelf life:

Store in original, unopened containers for 3 months at max. 25 °C

## **Technical Data**

Color trüb, farblos
Resin Acrylat-PU-Hybrid

#### **UNCURED PROPERTIES**

Viscosity(25 °C / Brookfield LVT /Sp.	/	UPM)	PE-Norm P001	1000 to 3000
Flash point [°C]			PE-Norm P050	> 100
Density [g/cm³]			PE-Norm P051	approx. 1.05

# Curing

UV(UV-A 40mW/cm²): [sec.] PE-Norm P002 5

#### **CURED PROPERTIES**

Temperature Resistance [°C]

Hardness Shore D PE-Norm P052 75 to 85
Water Absorption [Gew-%] PE-Norm P053 < 0,6

Our data sheets have been compiled to the best of our knowledge. The information included in our data sheets is exclusive information for the tended user and describes characteristics, with no declaration of commitment. We recommend trials in order to confirm that our products satisfy the particular application requirements. For an additional technical consultation, please contact our RD department. In general, for guarantee claims, please refer to our standard terms and conditions.

# Adhesives and more...

XP.08.83



## TECHNICAL DATASHEET

Vitralit® UD 8559

#### **Mechanical Data**

Elongation at Break [%]

[PE-Norm P060]

approx. 50

## Instructions for Use

#### Surface Preparation

The surfaces to be adhered should be free of dust, oil, fat or any other dirt in order to optimise reproducible bonds. Lightly soiled surfaces can be cleaned with cleaner IP, whereas substrates with low surface energy (such as polyethylene, polypropylene or Teflon) need to be treated physically using plasma or corona

to create a suitable working surface. For glass bonding applications we have developed a special primer pen which can be easy applied to prepare the surface for best results. Application

Our products are delivered ready for use. As soon as you receive them, you can dispense them, be it by hand from the container, or semi/fully automatically. When applied automatically, we recommend the use of air pressure with the appropriate cartridge/piston combination to dispense the adhesive at the required speed and accuracy. If help is required, please consult our engineering department

Please read the corresponding Safety Data Sheet for this product.

Adhesives and more...

XP.08.83

Otherwise the guidelines for application, storage etc. in our general Data Sheet Vitralit® are valid.

21.08.2009 / 21.08.2009 SIEGLINDE.HINSDORF

page 2