

MOLYKOTE® P-1500 (S) Paste

White grease-paste with solid lubricants

Features & benefits

- Wide service-temperature range (-50° to +160°C)
- High load-carrying capacity
- Good water resistance and water washout resistance
- Excellent protection against galling and fretting corrosion
- Prevents stick-slip and seizure
- No intentional polytetrafluoroethylene (PTFE) or per- and polyfluoroalkyl substances (PFAS)

Composition

- Semi-synthetic oil
- Lithium soap
- Solid lubricants
- Corrosion inhibitor

Applications

Assembly and long-term lubrication of metallic components. Sliding surfaces and friction contacts exposed to heavy loads, requiring "clean" lubrication, especially at low to medium speeds. Used on friction contacts of electrical and domestic appliances, packaging and office machinery, precision instruments, in textile and plastics processing machinery, and for lubrication of components in the automotive industry.

Description

MOLYKOTE® P-1500 (S) Paste is a white-colored grease-paste that combines the benefits of wide operating-temperature range with excellent anti-fretting properties. This paste can be used for assembly as well as for long-term lubrication of metallic components.

How to use

Clean points of contact. Apply in same way as lubricating greases, using brush, spatula, grease-gun or automatic lubricating device. Suitable for delivery by central lubricating system. Excess lubrication does not harm.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		
Consistency, density, viscosity			
ISO 2137	Unworked penetration	mm/10	285-315
ISO 2811	Density at 20°C	g/ml	1.05
DIN 51562	Base oil viscosity at 40°C	mm ² /s	90
Temperature			
	Service temperature range	°C	-50 to 160
ISO 2176	Dropping point	°C	≥ 170
DIN 51805	Flow pressure at -20°C/-40°C	mbar	< 500/< 1400
ASTM D1478-80	Low-temperature torque at -40°C		
	Initial break-away torque	Nm	< 300 x 10 ⁻³
	Torque after 20 min running time	Nm	< 100 x 10 ⁻³
Load-carrying capacity, wear protection			
	Four-ball tester		
DIN 51350 T4	Weld load	N	4,000
DIN 51350 T5	Wear scar under 800 N load	mm	0.76
	LFW-1 oscillating; no. of oscillations to $\mu = 0,12$ Load = 562 N, $v = 72$ cm/s	cycles	≥ 500,000
Almen-Wieland machine			
	OK load	N	20,000
	Friction force	N	1,650

⁽¹⁾ISO: International Organization for Standardization. DIN: Deutsche Industrie Norm. ASTM: American Society for Testing and Materials.

Continued on next page

Typical properties (continued)

Standard ⁽¹⁾	Test	Unit	Result
Coefficient of friction			
	Press-fit test	μ	0.12
ASTM D-7594-10	SRV, Fretting (100 N, 0.3 mm stroke), 8 h	μ	0.12
Water resistance and corrosion protection			
DIN 51807	Water resistance, 3 h, 90°C		0-90
DIN 51802	SKF Emcor, corrosion preventing properties		Max. 2

Oil separation

DIN 51817	Standard test 7 days, 40°C	%	6.5
-----------	----------------------------	---	-----

⁽¹⁾ISO: International Organization for Standardization. DIN: Deutsche Industrie Norm. ASTM: American Society for Testing and Materials.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored between 0 and 40°C in the original, unopened containers, MOLYKOTE® P-1500 (S) Paste has a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes as shown on molykote.com. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with™, SM or® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.

© 2025 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.